



## Vetotop CS535

Premixed 10 to 30 mm thick cementitious screed

### Uses

- Leveling of concrete slabs before the application of final floor coverings.
- Screeding over hollow-core pre-cast concrete slabs.
- Leveling floors and slabs to slope to ensure proper flow to drains.

### Product Description

Vetotop CS535 is a single component cementitious floor screed composed of hydraulic binders, silica sand, selected aggregates, special additives, and fibers. It is supplied as a dry powder in pre-weighed bags ready to use on-site; once mixed, it will form a trowelable mortar applied in thicknesses between 10 and 30 mm.

### Advantages

- Factory-controlled pre-blend ensures consistently high quality.
- Suitable for Middle East harsh weather conditions.
- Easy application enabling high productivity & superior finishing.
- Excellent physical and mechanical properties.
- Shrinkage compensated.
- Excellent workability.
- Fiber-reinforced resisting crack formation.

### Technical Data

Vetotop CS535	Typical Values
Appearance	Grey color powder
Aggregate size (mm)	0-3 mm
Application thickness	10 - 30 mm
Dry density (kg/liter)	1.70 approx.
Wet density (kg/liter)	2.10 approx.
Open time @ 25°C	30 min approx.
Compressive Strength (ASTM C109)	@ 1 day ≥ 5.5 MPa @ 3 days ≥ 16 MPa @ 28 days ≥ 40 MPa approx.
Water demand	13 - 16%

### Standards Compliance

- EN197: 2011
- EN13813:2002
- BS8204:2010
- ASTM C109

## Usage Instructions

### Surface Preparation

The surface should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.

### Priming

Vetotop CS535 can be laid as a bonded screed by applying Vetobond PB434 slurry to the prepared concrete substrate as a bonding and priming layer.

Alternatively, an epoxy bonding agent can be used, such as Vetobond EB430 or Vetobond EB431.

To prepare the slurry primer, mix 1 volume of Vetobond PB434 to 1 volume of clean water with 3 volumes of fresh cement and mix until achieving a smooth consistency. Scrub the mixed slurry into the concrete surface. While the slurry is wet, apply Vetotop CS535 to ensure good adhesion with the substrate.

### Mixing

For the mixture's preparation, pour into a container 6.5-8 liters of water for each 50Kg bag of Vetotop CS535.

Add the powder to the water and mix with a low-speed electric drill fitted with a suitable paddle until achieving a uniform, lump-free consistency mix. Do not add further water to the mix. Do not add water to the mix once it starts to set.

Add the required aggregate type to the mixed screed slowly while continuing mixing until a uniform consistency is achieved.

### Application

Pour the mixed material onto the surface and spread it to the desired thickness using a steel trowel or suitable tools.

### Curing

Cure the screed as per standard concrete curing practices. Do not subject the screed to vehicular traffic for 28 days till ensuring full cure and the system's ability to withstand designed traffic loads.

If a concrete sealer requires enhancing the screed durability

and resistance to water ingress, apply Vetoseal XW770 at a rate of 8 to 12 m<sup>2</sup> per liter. Make sure to apply the sealer uniformly and to cover all screed surfaces.

### Cleaning

Clean tools with water promptly before material hardens. Hardened material can be mechanically removed.

### Packaging & Coverage

Product	Pack Size	Yield
Vetotop CS535	50 Kg Bag	23.3 - 32.3 Ltr

Stated consumption data are for general guidance. Actual consumption depends on the nature of substrate, method of application, and wastage.

### Shelf Life & Storage

The original sealed bag of Vetotop CS535 has a shelf life of 12 months, provided it is stored clear of ground in a dry and shaded place, at temperatures between 5°C - 35°C.

### Limitations

- Do not apply the product at a temperature of less than +5°C.
- For further information contact our technical department.

### Health & Safety

Vetotop CS535 is highly alkaline; therefore, avoid direct contact with eyes or skin. Vetobond PB434 is a latex emulsion; it is recommended to use protective gloves and goggles during application.

Any skin contact should be washed with plenty amount of water. In case of eye irritation, immediately wash with a copious amount of clean cold water. Seek medical advice.

Vetotop CS535 is non-flammable.

For professional use only. Keep out of reach of children.

Due to continuous product improvements, the data mentioned in this document is subject to change without prior intimation. All recommendations and suggestions are therefore made without guarantee. Samples will be provided on request to enable customers to satisfy themselves as to the suitability of the product for any specific purpose and to assess the product under their own working conditions. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.